

Achieving Superosseointegration: The Photofunctionalization Effect

Yassir Abdelrahman Hag Elkhidir and Yang Cheng*

Department of Stomatology, Union Hospital, Tongji Medical College, Huazhong University of Science and Technology, China

*Corresponding author: Yang Cheng, Department of Stomatology, Union Hospital, Tongji Medical College, Huazhong University of Science and Technology, 1277, Jiefang Avenue, Wuhan 430022, Hubei, P.R. China, Tel: +008613517199412; E-mail: 2377615699@qq.com

Received Date: May 02, 2017; Accepted Date: May 09, 2017; Published Date: May 16, 2017

Copyright: © 2017 Cheng Y, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Abstract

Osseointegration is the backbone of successful implant stability. Biological ageing of titanium implants decreases its bioactivity leading to less bone to implant contact. Ultraviolet photofunctionalization reverses the ageing process, increases the bone-implant contact to almost 100% in what is known as "Superosseointegration", and therefore increasing the strength and the primary stability of implants while decreasing the healing time. Photofunctionalization was shown to improve the prognosis, decreased morbidity and to have a significant impact on clinical practice. The aim of this review is to explain the events on the molecular level, the clinical implications of photofunctionalization and to highlight some of the other applications associated with this new technology.

Keywords: Osseointegration; Photofunctionalization; Biological ageing

Osseointegration

OI is the "direct structural and functional connection between ordered living bone and the surface of the load - covering implant at the histological level [1-3]. When this bone opposition occurs, without any soft tissue intervention between the bone and the implant surface, it translates clinically into a long-term rigid, stable fixation of implants into the surrounding bone [2]. Osseointegration is a prerequisite for primary implant stability and is by far the most important factor to consider before establishing any further treatment [3]. Knowing the biological events and the healing process occurring after placing an implant is therefore significant for further understanding of the different factors acting on this bone-implant interface.

Mechanism of Osseointegration

The process of bone formation involves attachment, settlement, proliferation, and maturation of osteoblasts followed by mineralisation around the secreted proteins [4]. Similar to primary bone healing, there is a cascade of biological events occurring around the implant fixture. The wound healing process starts within a few seconds of blood contact on the implant surface. Thrombocytes initiate the coagulation cascade, and then inflammatory cytokines along with other growth factors and vasoactive amines are released leading to the migration and proliferation of phagocytic cells. Neutrophils peak at the first three days following surgery to remove the dead cells and residues of bacterial extracellular matrix. Macrophages follow to help in the degradation process and express more cytokines, inducing further recruitment of osteogenic and endothelial progenitors [5]. Angiogenesis within the fibrin matrix occurs simultaneously with removal of coagulum. The formed fibrin matrix acts as a scaffold for colonisation of the migrating and differentiation of osteogenic cells such as osteoblasts and the recruited mesenchymal stem cells (MSCs) arriving as early as the first day. Upon arrival of these osteoprogenitor cells, matrix formation and mineralisation initiates by contact osteogenesis [2,3]. Following osteoid deposition on the implant

surface, immature woven bone starts remodelling at the second week and becomes replaced by mature lamellar bone within three months [5] as shown in Figure 1.

Titanium

In the recent decades, Implant biomaterials have been widely investigated, aiming at finding and developing the most biocompatible implants biomaterials which can achieve high levels of OI and implant stability. Despite exhibiting better biocompatible nature and less foreign body reaction compared to other conventional materials [3,6] pure titanium and titanium alloys were found to also have good mechanical reliability, high corrosion resistance, as well as exhibiting low modulus of elasticity and considerable fatigue strength [7,8]. These excellent mechanical and superior physiochemical properties makes titanium much more favourable than other alloys like stainless steel or chrome-cobalt in regards to biocompatibility and clinical choice.

Tissue response is largely dependent on the nature of the implant surface. Unlike bioactive surfaces which participates actively in OI, bioinert surfaces does not play a role in this process [9]. Titanium and titanium alloys are considered bioinert according to their surface oxides, so the OI on their surfaces occur due to a lack of negative tissue response rather than occurring due to a positive one [3]. Titanium implant surfaces are osteoconductive and allows bone growth on its surface by distant osteogenesis [3]. Surface modification approaches have been focused on making it more osteoinductive in order to stimulate and recruit osteogenic cells and to exhibit contact osteogenesis [10].

Biological Aging of Titanium

The term biological ageing refers to the time-related degradation of the physiochemical properties of the implant surface [11-16]. It is well documented that following a sufficient healing period after placing titanium implants, the osseointegration level is usually less than ideal and the BIC does not reach 100% [12,13].




Figure 1: Schematic illustration of the process of osseointegration around the implant surface. 1) Serum proteins form a layer on the implant surface, 2) Clot formation and inflammatory process begin. Neutrophils remove debris and dead cells from the Extracellular matrix, cytokines released from platelets and further by macrophages are responsible for recruitment of osteogenic and endothelial progenitors (Osteoblasts, hMSCs, fibroblasts). 3) Angiogenesis starts simultaneously with the removal of the blood clot, and bone starts forming at the implant surface. 4) Osteoid becomes woven bone within 2 weeks and gets replaced by lamellar bone within 3 months.

This phenomenon is largely attributed to the unavoidable deposition of carbon from the atmosphere forming a layer of hydrocarbon on the titanium surface leading to significant loss of the hydrophilicity and surface charge from the implant surface. This causes impairment of the physicochemical and biological capabilities, resulting in a substantial decrease in osteoconductivity, poor osteogenic recruitment and proliferation as well as reduced absorption of serum proteins [17-19].

Extracellular matrix (ECM) serum proteins play a major role in accelerating osteoinduction and bone integration [20-22]. However, the affinity of these negatively charged serum proteins to the implant becomes severely affected by the gradual time-dependent change of the surface from positive to negative on the aged titanium surfaces [22-26]. As a result, the amount of bone covering implants and the strength of initial fixation is reduced to less than half compared to those seen in new surface [18].

Photofunctionalization

Light wavelengths visible to the human eyes ranges from 400 to 700 nm. Ultraviolet (UV) light on the other hand can be either UVA (320-400 nm), UVB (290-320 nm) or UVC (10-290 nm). The range used in biological investigations is 200-400 nm [27]. UVA light can remove hydrocarbons through inducing TiO₂ photocatalysis [28]. UVC irradiation is considered superior in reducing the surface carbon levels, improving the hydrophilicity and enhancing the protein adsorption and cell function [29,30].

Ultraviolet (UV) PhF is the surface modification changes on titanium surfaces following UV treatment, including the alteration of physicochemical properties and the enhancement in biologic capability. It is a unique and simple mechanism which remarkably increases the biologic capacity of titanium implants and enhances osseointegration to nearly 100% BIC (Superosseointegration) compared to less than 55% for untreated implants [11,12,31,32].

PhF improves protein affinity to the implant surface, and drastically enhances physiological function as well as the expression of osteogenic cells phenotypes [11,18,19,32,33]. This “upgrade” in the OI capacity at the implant surfaces is caused fundamentally by inducing three property changes on the titanium implant surface:

- PhF regenerates the lost hydrophilicity caused by biological age ing of titanium, it converts titanium surfaces from hydrophobic to “Superhydrophilic” [12-15].
- It optimises the electrostatic status of the surface, reverting it from electronegative back to original electropositive status found on fresh titanium surfaces [18,19].
- It removes the significant amount of hydrocarbon that unavoidably accumulates on the surface by time (Figure 2) [31-33].

Hydrophilicity

Although the wettability of titanium surface is not an indicator of it’s bioactivity, recent studies demonstrated that hydrophilicity and electric charge play key roles in the initial attachment of cells to UV-functionalized titanium [29,34]. A newly processed titanium surface is “superhydrophilic”. This term is used when the contact angle of water to the surface is less than 5 degrees. Due to ageing of titanium, the implant surface gradually becomes hydrophobic with a contact angle more than 60 degrees after 4 weeks of processing [29]. UV treatment converts the aged surface from hydrophobic to superhydrophilic in conjunction with the removal of hydrocarbon contamination from the titanium’s surface. The bioactivity of a UV-treated of 4 week old titanium surfaces becomes even higher than that of a newly processed surfaces [16,34].

Electrostatic status

UV-treated titanium surfaces are electropositive, whereas aged titanium surfaces are electronegative [18]. PhF of titanium oxide (TiO₂) causes excitement of an electron from valence band to conduction band and creates a positive hole on the superficial layer [19]. This results in the conversion of relevant Ti⁴⁺ sites to Ti³⁺ sites which are favourable for dissociative water adsorption to form basic Ti-OH groups [28,31]. The surface oxygen vacancies eliminate the need for inorganic bridges for cell attachment and adhesion and hence, enabling direct protein–titanium interaction or even a direct cell–titanium interaction. UV treatment, therefore results in more cells

attraction and stronger cell adhesion by converting the titanium surface from bioinert to bioactive [19].

Hydrocarbon removal

In contrast to other techniques aimed at modifying the surface topography of implants, such as oxidising, sandblasting, acid etching [35,36]. UV treatment does not Alter the topography, but it rather removes the surface hydrocarbons which are responsible for biological ageing. The surface of bulk titanium is made of a semiconductor TiO_2 . Therefore, UV treatment removes hydrocarbons by induced photocatalytic activity of TiO_2 and a direct decomposition by UV. The removal of hydrocarbon results in the exposure of Ti^{4+} and may facilitate its interaction with biological cells that are electronegatively charged [28,31]. The level of hydrocarbons on the TiO_2 surface is inversely related to the level of protein absorption and osteoblast attachment [18,33].




Figure 2: Schematic comparison between the physiochemical properties of the titanium's surface as received "aged" and the titanium's surface following PhF. A) Photofunctionalized surface shows much higher wettability across the implant surface than the non-treated surface. B) The surface charge on the UV treated surface becomes positive, allowing the negatively charged osteoblasts and stem cells to attach alone or through serum proteins. The non-treated surface is negatively charged and the only method of cells to attach is via bridging divalent cations (Mg^{++} , Ca^{++}). Monovalent cations (Na^+ and K^+) competitively inhibit cell attachment. C) Photofunctionalization removes the hydrocarbon layer from the surface allowing for more protein absorption, and better attachment and spread of osteoblasts.

UV Effect at the Molecular Level

Studies have shown that PhF of titanium surfaces increases protein absorption, enhances osteogenic migration and attachment, as well as osteoblastic proliferation and differentiation [12,19,34-41].

Protein adsorption

Biocompatibility of any material is highly dependent on the capacity of protein adsorption on its surface [18]. Adhesive ECM proteins and transmembrane cellular receptors mediate cell attachment to titanium surfaces [29]. ECM fibronectin interacts with cell membrane integrins to facilitate osteoblastic adhesion and proliferation on the implant surface [12,19]. Vinculin is a cell-binding membrane cytoskeletal

protein that binds (via other adhesion complex proteins) to integrins and actin filaments [37], which are cell adhesion membrane filaments that are highly essential in the establishment of cell adhesion and in cytoskeletal development [38,39]. Integrins are transmembranous "bridging" receptors. They bind to ECM proteins such as fibronectin and collagen and initiate cell attachment by ligand-specific RGD peptide interactions [40,41]. Actin is a major constituents of stress fibres which largely forms lamellipodia and filopodia extensions. Actin filaments also maintains cellular shape and are responsible for tension resistance [34,39]. The loss of vinculin prevents cell adhesion and spreading, stress fiber formation, and cellular extensions (Figure 3) [42,43].

Albumin on the other hand serves a carrier for molecules and plays a role in the metabolism of vitamin D in osteoblasts [44]. Albumin also regulates cytoplasmic calcium and stimulates osteoblast proliferation [19,40,45]. Calcium regulation is important for attraction of anionic proteins because titanium surfaces have a net negative charge and must therefore first be bridged by divalent cations to compete with monovalent cations, such as Na^+ and K^+ which might block the anion sites, making a large part of the titanium surface bioinert for proteins and cells. However, although albumin enhances the fibronectin-integrin interactions [46]. Albumin itself is a competitive inhibitor to cell attachment [47-49], and it gets gradually replaced by fibronectin in reaction to the increased hydrophilicity following UV treatment (Figure 2) [50].

The amount of protein adsorption is inversely correlated with the amount of hydrocarbon on titanium surfaces [33]. Protein adsorption drops to less than 50% in aged titanium surfaces. PhF of titanium surfaces causes a substantial increase in protein expression not only compared to aged implant surfaces but to new surfaces as well [12,19,34].


Osteoblast Attachment and Spreading

The initial attachment and spreading of osteoblasts is affected by the surface properties of different implant biomaterials [51,52] and it plays a critical role in OI [29]. Failure of cell attachment and spread on titanium surfaces leaves the cells undifferentiated and suspended in a circular form [53-56]. Adhesion of osteoblasts is regulated by the Rho family GTPases. These are signaling G proteins which play an important role in the dynamics of intracellular actin leading to assembly of stress fibres and in turn, contributes to the osteoblastic mobility and adhesive affinity to the titanium surface [34].

Biological ageing causes the number of attached osteoblasts to be reduced by about 50% and the spread of osteoblasts becomes noticeably delayed [12-15]. UV treatment restores the hydrophilicity and the electrostatic status of the surfaces leading to enhanced formation of focal adhesion complexes and the subsequent GTPase protein gene expression, causing a subsequent increase in the quality and quantity of osteoblastic adhesion and spreading.

Osteoblast Differentiation and Mineralization

Proper OI requires a well-mineralized matrix around the implant surfaces. The recruited osteogenic cells should be completely matured and differentiated in order to produce bone matrix and then mineralize. Alkaline phosphatase (ALP) is a byproduct and an indicator of maturing osteoblastic activity. Elevated levels of this enzyme are suggestive of enhanced osteogenic activity and active bone deposition [13,29].



Despite the drastic reduction of the total ALP activity on aged titanium surfaces by more than 50% [13,57] the cell-based ALP activity and osteoblastic gene expressions are not affected significantly. This indicates that the decreased levels of ALP activity and cell differentiation is actually due to the overall inhibition of osteoblastic attachment and proliferation [34] rather than biological ageing process itself. The increased rates of protein absorption and osteoblastic adhesion and proliferation on photofunctionalized titanium surfaces are therefore the reason behind the increased number of differentiated cells on the implant surface, as well as the increased matrix deposition and mineralisation.

Antibacterial effect of PhF

Preventing colonisation of bacteria on the implant surface is critical. However, bacterial contamination of implant surfaces during surgery is unavoidable. There are billions of bacteria in the oral cavity and over 600 different species [58,59]. Furthermore, a portion of the implant is positioned transmucosally during the healing period and is exposed to bacteria which is very similar to those found in periodontal disease [60,61]. These bacteria can utilise salivary and blood proteins to enhance their attachment on the implant surface [62-64]. Elimination of pathogenic microorganisms from implant surfaces is essential to avoid implant failure. Ultraviolet disinfection has been proven to effectively eradicate numerous bacterial species [65-70].

The bacterial charged cell surface interacts with the charged molecules or ions on the surface of implants. UV treatment of TiO₂ reduces the population of oral bacteria attached to the surface by roughly more than 3 folds during the first 6 hours following implant placement. This is the critical period prior to the formation of the blood clot which acts as a barrier to bacterial access, and also when the freshly implanted fixture is still highly susceptible to bacterial colonisation. Enhanced UV-mediated osteogenic adhesion to the implant surface causes osteoblasts to compete with microorganisms for space and competitively inhibit the bacterial capacity to proliferate and attach to the implant surface [69]. UV treatment reduces the biomass and decreases the area covered by the bacterial biofilm and hence, reduces the risk of implant infection and failure [71].

Clinical significance of PhF

Time-related biological degradation of titanium surfaces has an adverse effect on the osseointegration capacity and subsequently on the whole healing process. The amount of BIC gets reduced significantly due to biological ageing of titanium. PhF of dental implants prior to their placement reverses the ageing process and results in direct bone formation on the implant surface “Contact Osteogenesis” [72]. UV treatment of titanium surfaces increases the BIC from 55% to a near maximum level of 98.2% [11,12,31,73-75] and also leads to a 3-fold increase in the strength of bone-implant integration. This highly enhances the primary stability, even in implants placed without cortical bone support. The initial stability is crucial in avoiding micromovements which may adversely affect the osseointegration process [72].

Implant stability quotient (ISQ) is a reliable and a valid method for measuring the primary stability [75-78]. The Push-in value is the breakage strength of osseointegration while the implant is being pushed. Both ISQ and Push-in values were higher in UV treated surfaces than not only aged titanium, but to new “as-received” titanium surfaces [73]. Implants show better load distribution and the mechanical stress in the peri-implant marginal bone is reduced [11,12,22,31,29]. Furthermore, the osseointegration process occurs 4 times faster and the average healing time required before functional loading reduces by one half compared to the non-photofunctionalized implants [11,31,74].

PhF allows for a quicker loading protocol and a decreased overall treatment time. It also permits the use of shorter and small-diameter implants without compromising the success rate [74]. This opens new treatment possibilities for the use of these smaller implants in more complex cases with higher load or space requirements.

Implant’s “Stability dip” is a term used for the weakest stability point throughout the healing period which occurs typically 3 weeks following implant placement due to the osteoblast and osteoclast turnover and bone remodelling. Due to the significant improvement in the OI process, UV treatment of Titanium surfaces eliminates the stability dip, leading to a better and more predictable treatment outcome [79].

Other applications

Other technologies can be incorporated successfully with UV PhF. Nanotechnology is an attractive science with promising applications in the dental field [80]. There is an increasing trend to develop implant surface topographies on a nanoscale level in order to increase its osteoconductivity [81,82] and enhance the osseointegration process [83-86]. Nanomodification can be done via various approaches such as ion beam deposition, nanoparticle compaction, acid etching, anodising, peroxidation, or chemical conjugation of biomolecules [81,87,88]. Most approaches aim to mimic tissue components by applying nanotopographies such as nanonodules (Figure 4) and nanotubes to the implant surface. Similar to PhF, these “biomimetic” surface features alter the surface interactions with biomolecules and improve the cell adhesion properties [81,89-91]. Hence, it remarkably enhances osteoblastic behaviour and responses, cell attachment, proliferation, alkaline phosphatase activity, and improves protein absorption [67,83,92-95]. Leading to rapid bone healing. Clinically, biomimetic surfaces significantly increases the BIC, strengthens implant fixation up to a 70%, and reduces soft tissue intervention [91]. Combining UV photofunctionalization to these nanoscale

topographies has been shown to provide a synergistic advantage [83,96]. For instance, fluoride treatment or microarc oxidation (MAO) of implant surfaces alone have shown to improve cellular response and bone formation around the implant [97,98], but adding UV light to the

equation further enhances cellular bioactivity and human mesenchymal stem cells (hMSCs) attachment to the implant surface leading to even stronger and a more accelerated osseointegration [82,93,99,100].




Figure 4: PhF effect on titanium and tissue, and clinical significance.

UV PhF can be utilised in various dental fields. Similarly to the dental implant fixtures, orthodontic miniscrews can also benefit from PhF. The overall success rate of orthodontic miniscrews is around 72% for 6-mm and 8-mm long miniscrews 90% [101,102]. Wider and longer screws provide better anchorage but usually the space for their placement is usually limited, and larger screws are more difficult to remove. Photofunctionalized mini screws were found to provide better anchorage and they displace much less under lateral tipping forces [101]. Photofunctionalization was also found to be effective in increasing the osteoconductivity of titanium mesh and enhancing bone regeneration around it in augmentation procedures [103]. Moreover, UV treatment can also be used to increase the cellular activity and protein adhesion in more advanced tissue engineering techniques such as cell sheet technology [104], which is used to deliver cells in single-sheet form reinforced by a micro-thick titanium framework [105].

Some non-titanium materials were found to be similarly affected by the UV-mediated reversal of biological ageing. UV treatment was associated with a decreased amount of surface carbon in aged chromium-cobalt alloy [29] as well as in zirconium [12], which is a promising alternative material for dental implants because of their mechanical stability, biocompatibility, low plaque attachment, good esthetics and soft tissue compatibility [106-108]. However, low temperature degradation (LTD) is considered a major limitation of this material [109,110], and the oxide layer found on native zirconia makes it bioinert. UV treatment reduces amount of surface carbon, converts zirconium from hydrophobic to hydrophilic and significantly improves the bioactivity of zirconia [111,112].




Figure 5: Adding nanoparticles increases the surface area for cellular attachment and enhances cellular bioactivity.

Conclusions

The concept of Superosseointegration is a major breakthrough towards achieving better implant stability and better implant treatment outcomes. PhF increases the implant's primary stability significantly leading to a higher implant success rates and a decreased average healing time. It also allows for more treatment options as shorter and thinner implants can be utilized more frequently without any compromise to the treatment outcome. Further research should be applied for incorporating ultraviolet surface treatment to other dental materials. The clinical ease, low cost of application and significant impact on treatment should also encourage the manufacturers to develop PhF devices affordable for most clinicians.

References

- Jayesh RS, Dhinakarsamy V (2015) Osteointegration. *J Pharm Bioallied Sci* 7: 226-229.
- Mavrogenis AF, Dimitriou R, Parvizi J, Babis GC (2009) Biology of implant osseointegration 9: 61-72.
- Ramazanoglu M, Oshida Y (2011) Osseointegration and Bioscience of Implant Surfaces - Current Concepts at Bone-Implant Interface; *Implant Dentistry - A Rapidly Evolving Practice*, InTech.
- Ogawa T (2010) Photofunctionalization of TiO₂ for optimal bone-titanium integration: A novel Phenomenon of Superosseointegration; *Environmentally Benign Photocatalysts*. New York: Springer 699-713.
- Davies JE (1998) Mechanisms of endosseous integration. *Int J Prosthodont* 11: 391-401.
- Gao Y, Liu Y, Zhou L, Guo Z, Rong M, et al. (2013) The Effects of Different Wavelength UV Photofunctionalization on Micro-Arc Oxidized Titanium. *PLoSOne* 8.
- Niinomi M, Liu Y, Nasaki M, Liu H, Li H (2016) Biomedical titanium alloys with Young's moduli close to that of cortical bone. *Regen Biomater* 3: 173-185.
- Lee JH, Ogawa T (2012) The Biological Aging of Titanium Implants. *Implant Dent* 21: 415-421.
- Parkash RB, Shetty O, Tabassum R (2012) Surface modifications of Endosseous dental implants. *Int J Oral implantol Clin Res* 3: 116-121.
- Albrektsson T, Johansson C (2001) Osteoinduction, osteoconduction and osseointegration. *Eur Spine J* 2: 96-101.
- Ogawa T (2012) UV photofunctionalization of titanium implants. *J Craniofac Tissue Eng* 2: 151-158.
- Att W, Ogawa T (2012) Biological aging of implant surfaces and their restoration with ultraviolet light treatment: A novel understanding of osseointegration. *Int J Oral Maxillofac Implants* 27: 753-761.
- Lee JH, Ogawa T (2012) The biological aging of titanium implants. *Implant Dent* 21:415-421.
- Suzuki T, Hori N, Att W, Kubo k, Iwasa F, et al. (2009) Ultraviolet treatment overcomes time-related degrading bioactivity of titanium. *Tissue Eng A* 15: 3679-3688.
- Iwasa F, Tsukimura N, Sugita Y, Att W, Kodali-Kanuru R, et al. (2011) TiO₂ micro-nano-hybrid surface to alleviate biological aging of UV-photofunctionalized titanium. *Int J Nanomedicine* 6: 1327-1341.
- Hori N, Ueno T, Suzuki T, Yamada M, Att W, Okada S, et al. (2010) Ultraviolet light-treatment for the restoration of age-related degradation of titanium bioactivity. *Int J Oral Maxillofac Implants* 25: 49-62.
- Hori N, Ueno T, Minamikawa H (2010) Electrostatic control of protein adsorption on UV-photofunctionalized titanium. *Acta Biomater* 6: 4175-4180.
- Iwasa F, Hori N, Ueno T (2010) Enhancement of osteoblast adhesion to UV-photofunctionalized titanium via an electrostatic mechanism. *Biomaterials* 31: 2717-2727.
- Rapuano BE, Lee JJ, MacDonald DE (2012) Titanium alloy surface oxide modulates the conformation of adsorbed fibronectin to enhance its binding to integrins in osteoblasts. *Eur J Oral Sci* 120: 185-194.
- Rapuano BE, MacDonald DE (2011) Surface Oxide Net Charge of a Titanium Alloy ; Modulation of Fibronectin-Activated Attachment and Spreading of Osteogenic Cells. *Colloids Surf B Biointerfaces* 82: 95-103.
- Rapuano BE, Hackshaw KM, Schniepp HC, MacDonald DE (2012) Effects of Coating a Titanium Alloy with Fibronectin on the Expression of Osteoblast Gene Markers in the MC3T3 Osteoprogenitor Cell Line. *Int J Oral Maxillofac Implants* 27: 1081-1090.
- Tsai JA, Lagumdzija A, Stark A (2007) Albumin-bound lipids induce free cytoplasmic calcium oscillations in human osteoblast-like cells. *Cell Biochem Funct* 25: 245-249.
- Klinger A, Steinberg D, Kohavi D, Sela MN (1997) Mechanism of adsorption of human albumin to titanium in vitro. *J Biomed Mater Res* 36: 387-392.
- Bagambisa FB, Kappert HE, Schilli W (1994) Cellular and molecular biological events at the implant interface. *J Craniomaxillofac Surg* 22: 12-17.
- Flanagan D (2016) Photofunctionalization of Dental Implants, *J Oral Implantol* 42: 445-450.
- Att W, Hori N, Iwasa F, Yamada M, Ueno T, et al. (2009) The effect of UV-photofunctionalization on the time-related bioactivity of titanium and chromium-cobalt alloys. *Biomaterials* 30: 4268-4276.
- Shie JL, Lee CH, Chiou CS, Chang CT, Chang CC, et al. (2008) Photodegradation kinetics of formaldehyde using light sources of UVA, UVC and UVLED in the presence of composed silver titanium oxide photocatalyst. *J Hazard Mater* 155: 164-172.
- Aita H, Hori N, Takeuchi M (2009) The effect of ultraviolet functionalization of titanium on integration with bone. *Biomaterials* 30: 1015-1110.
- Suzuki S, Kobayashi H, Ogawa T (2013) Implant Stability Change and Osseointegration Speed of Immediately Loaded Photofunctionalized Implants. *Implant Dent* 22: 481-490.
- Att W, Hori N, Takeuchi M (2009) Time-dependent degradation of titanium osteoconductivity: An implication of biological aging of implant materials. *Biomaterials* 30: 5352-5363.
- Iwasa F, Baba K, Ogawa T (2016) Enhanced intracellular signaling pathway in osteoblasts on ultraviolet light-treated hydrophilic titanium. *Biomed Res* 37: 1-11.
- Le Guehennec L, Soueidan A, Layrolle P, Amouriq Y (2007) Surface treatments of titanium dental implants for rapid osseointegration. *Dent Mater* 23: 844-854.
- Sykaras N, Iacopino AM, Marker VA, Triplett RG, Woody RD (2000) Implant materials, designs, and surface topographies: Their effect on osseointegration. A literature review. *Int J Oral Maxillofac Implants* 15: 675-690.
- Parsons JT, Horwitz AR, Schwartz MA (2010) Cell adhesion: integrating cytoskeletal, dynamics and cellular tension. *Nat Rev Mol Cell Biol* 11: 633-643

35. Humphries JD, Wang P, Streuli C, Geiger B, Humphries MJ, Ballestrom C (2007) Vinculin controls focal adhesion formation by direct interactions with talin and actin. *J Cell Biol* 179: 1043-1057.
36. Wen KK, Rubenstein PA, Demali KA (2009) Vinculin nucleates actin polymerization and modifies actin filament structure. *J Biol Chem* 284: 30463-30473.
37. Klinger A, Steinberg D, Kohavi D, Sela MN (1997) Mechanism of adsorption of human albumin to titanium in vitro. *J Biomed Mater Res* 36: 387-392.
38. Ellingsen JE (1991) A study on the mechanism of protein adsorption to TiO₂. *Biomaterials* 12: 593-596.
39. Goldmann WH, Ingber DE (2002) Intact vinculin protein is required for control of cell shape, cell mechanics, and rac-dependent lamellipodia formation. *Biochem Biophys Res Commun* 290: 749-755.
40. Ezzell RM, Goldmann WH, Wang N, Parashurama N, Ingber DE (1997) Vinculin promotes cell spreading by mechanically coupling integrins to the cytoskeleton. *Exp Cell Res* 231: 14-26.
41. Tsai JA, Lagumdzija A, Stark A, Kindmark H (2007) Albumin-bound lipids induce free cytoplasmic calcium oscillations in human osteoblast-like cells. *Cell Biochem Funct* 25: 245-249.
42. Mata A, Su X, Fleischman AJ, Roy S, Banks BA, et al. (2003) Osteoblast attachment to a textured surface in the absence of exogenous adhesion proteins. *IEEE Trans Nanobioscience* 2: 287-294.
43. Pols HA, Schilte HP, Nijweide PJ, Visser TJ, Birkenhager JC (1984) The influence of albumin on vitamin D metabolism in fetal chick osteoblast-like cells. *Biochem Biophys Res Commun* 125: 265-272.
44. Al Jawad M, Fragneto G, Liu J, Chang SR, Clarkson B (2009) Fibronectin adsorption studied using neutron reflectometry and complementary techniques. *Eur Phys J E Soft Matter* 30: 175-179.
45. Dewez JL, Doren A, Schneider YJ, Rouxhet PG (1999) Competitive adsorption of proteins: key of the relationship between substratum surface properties and adhesion of epithelial cells. *Biomaterials* 20: 547-559.
46. Pendegrass CJ, El-Husseiny M, Blunn GW (2012) The development of fibronectin-functionalised hydroxyapatite coatings to improve dermal fibroblast attachment in vitro. *J Bone Joint Surg Br* 94: 564-569
47. Mischa Z, Darren A, Morgan RA, Noah AR (2007) The role of albumin and fibronectin in the adhesion of fibroblasts to plasma polymer surfaces. *Plasma Process Polym* 9: 149-156
48. Arima Y, Iwata H (2007) Effect of wettability and surface functional groups on protein adsorption and cell adhesion using well-defined mixed self-assembled monolayers. *Biomaterials* 28: 3074-3082.
49. Miyata K, Takebe J (2013) Anodized-hydrothermally treated titanium with a nanotopographic surface structure regulates integrin- α 6 β 4 and laminin-5 gene expression in adherent murine gingival epithelial cells. *J Prosthodont Res* 57: 99-108.
50. Iwasa F, Hori N, Ueno T, Minamikawa H, Yamada M, et al. (2010) Enhancement of osteoblast adhesion to UV photofunctionalized titanium via electrostatic mechanism. *Biomaterials* 31: 2717-2727
51. Bik EM, Long CD, Amitage GC, Loomer P, Emerson J, et al. (2010) Bacterial diversity in the oral cavity of 10 healthy individuals. *ISME J* 4: 962-947.
52. Siqueira JF Jr, Fouad AF, Rocas IN (2012) Pyrosequencing as a tool for better understanding of human microbiomes. *J Oral Microbiol* 4.
53. Safii SH, Palmer RM, Wilson RF (2010) Risk of implant failure and marginal bone loss in subjects with a history of periodontitis: a systematic review and metaanalysis. *Clin Implant Dent Relat Res* 12: 165-174.
54. Mombelli A, Muller N, Cionca N (2012) The epidemiology of peri-implantitis. *Clin Oral Implants Res* 23: 67-76.
55. Jin L, Guo W, Xue P, Gao H, Zhao M, et al. (2015) Quantitative assay for the colonization ability of heterogeneous bacteria on controlled nanopillar structures. *Nanotechnology* 26: 055702.
56. Cavalcanti IM, Ricomini FAP, Lucena-Ferreira SC, Da Silva WJ, Paes LemeAF, et al. (2014) Salivary pellicle composition and multispecies biofilm developed on titanium nitrided by cold plasma. *Arch Oral Biol* 59: 695-703.
57. Badihi Hauslich L, Sela MN, Steinberg D, Rosen G, Kohavi D (2013) The adhesion of oral bacteria to modified titanium surfaces: role of plasma proteins and electrostatic forces. *Clin Oral Implants Res* 24: 49-56.
58. Rileya DJ, Bavastrello V, Covanib U, Baroneb A, Nicolinia N (2005) An in-vitro study of the sterilization of titanium dental implants using low intensity. *Dental Materials* 21: 756-760.
59. Einarsson E, Staffan, Svard SG, Karin Troell K (2015) UV irradiation responses in *Giardia intestinalis*. *Exp Parasitol* 154: 25-32.
60. Barbut F (2015) How to eradicate *Clostridium difficile* from the Environment. *J Hosp Infect* 89: 287-295.
61. Enwemeka CS, Williams D, Enwemeka SK, Hollosi S, Yens D (2009) Blue 470-nm Light Kills Methicillin-Resistant *Staphylococcus aureus* (MRSA) in Vitro. *Promoted Laser Surg* 27: 221-226.
62. Gallardo-Moreno AM, Pacha-Olivenza MA, Saldana L, Perez-Giraldo C, Brugue JM, et al. (2009) In vitro biocompatibility and bacterial adhesion of physico-chemically modified Ti6Al4V surface by means of UV irradiation. *Acta Biomater* 5: 181-192.
63. Yamada Y, Yamada M, Ueda T, Sakurai K (2014) Reduction of biofilm formation on titanium surface with ultraviolet-C pre-irradiation. *Biomater Appl* 29: 161-171.
64. De Avila ED, Lima BF, Sekiya T, Toril Y, Ogawa T Shi W, et al. (2015) Effect of UV-photofunctionalization on oral bacterial attachment and biofilm formation to titanium implant material. *Biomaterials* 67: 84-92.
65. Hirota M, Ozawa T, Iwai T, Ogawa T, Tohnai I (2016) Implant Stability Development of Photofunctionalized Implants Placed in Regular and Complex Cases: A Case-Control Study. *Int J Oral Maxillofac implants* 31: 676-86.
66. Suzuki S, Kobayashi H, Ogawa T (2013) Implant Stability Change and Osseointegration Speed of Immediately Loaded Photofunctionalized Implants. *Implant Dent* 22: 481-490.
67. Funato A, Yamada M, Ogawa T (2013) Success Rate, Healing Time, and Implant Stability of Photofunctionalized Dental Implants. *Int J Oral Maxillofac implants* 28: 1261-1271.
68. Ogawa T (2010) Photofunctionalization of TiO₂ for optimal integration of titanium with bone. In: Kamat P, Anpo M, eds. *Benign Photocatalysts. Applications of Titanium Oxide-based Materials*. New York: Springer 699-713.
69. Meredith N, Alleyne D, Cawley P (1996) Quantitative determination of the stability of the implant-tissue interface using resonance frequency analysis. *Clin Oral Implants Res* 7: 261-267.
70. Huang HL, Tsai MT, Su KC (2013) Relation between initial implant stability quotient and bone-implant contact percentage: An in vitro model study. *Oral Surg Oral Med Oral Pathol Oral Radiol* 116: 356-361.
71. Park KJ, Kwon JY, Kim SK (2012) The relationship between implant stability quotient values and implant insertion variables: A clinical study. *J Oral Rehabil* 39: 151-159.
72. Ueno T, Yamada M, Suzuki T (2010) Enhancement of bone-titanium integration profile with UV-photofunctionalized titanium in a gap healing model. *Biomaterials* 31: 1546-1557.
73. Nishimura I, Huang Y, Butz F, Ogawa T, Lin A, et al. (2007) Discrete deposition of hydroxyapatite nanoparticles on a titanium implant with predisposing substrate microtopography accelerated osseointegration. *Nanotechnology* 18: 1-9.
74. Mendonca G, Mendonca DB, Aragao FJ, Cooper LF (2008) Advancing dental implant surface technology—From micron- to nanotopography. *Biomaterials* 29: 3822-3835.
75. Ikeda T, Hagiwara Y, Hirota M, Tabuchi M, Yamada M, et al. (2014) Effect of photofunctionalization on fluoride-treated nanofeatured titanium. *J Biomater Appl* 28: 1200-1212.
76. Tsukimura N, Ueno T, Iwasa F (2011) Bone integration capability of alkali- and heat-treated nanobimorphic Ti-15Mo-5Zr-3Al. *Acta Biomater* 7: 4267-4277.

78. Mendonca G, Mendonca DB, Aragao FJ, Cooper LF (2008) Advancing dental implant surface technology - from micron- to nanotopography. *Biomaterials* 29: 3822-3835.
79. Svanborg LM, Andersson M, Wennerberg A (2010) Surface characterization of commercial oral implants on the nanometer level. *J Biomed Mater Res B Appl Biomater* 92: 462-469.
80. Kubo K, Tsukimura N, Iwasa F, Ueno T, Saruwatari L, et al. (2009) Cellular behavior on TiO₂ nanonodular structures in a micro-to-nanoscale hierarchy model. *Biomaterials* 30: 5319-5329.
81. Heo DN, Ko WK, Lee HR, Lee SJ, Lee D, et al. (2016) Titanium dental implants surface-immobilized with gold nanoparticles as osteoinductive agents for rapid osseointegration. *J Colloid Interface Sci* 469: 129-137.
82. Le Guéhennec L, Soueidan A, Layrolle P, Amouriq Y (2007) Surface treatments of titanium dental implants for rapid osseointegration. *Dent Mater* 23: 844-854.
83. Sanchez C, Arribart H, Guille MM (2005) Biomimetism and bioinspiration as tools for the design of innovative materials and systems. *Nat Mater* 4: 277-288.
84. Spatz JP (2002) Nano- and micropatterning by organic-inorganic templating of hierarchical self-assembled structures. *Angew Chem Int Ed Engl* 41:3359-62.
85. Kubo K, Tsukimura N, Iwasa F (2009) Cellular behavior on TiO₂ nanonodular structures in a micro-to-nanoscale hierarchy model. *Biomaterials* 30: 5319-5329.
86. Dalby MJ, Gadegaard N, Curtis AS, Oreffo RO (2007) Nanotopographical control of human osteoprogenitor differentiation. *Curr Stem Cell Res Ther* 2: 129-138.
87. Jager M, Zilkens C, Zanger K, Krauspe R (2007) Significance of nano- and microtopography for cell-surface interactions in orthopaedic implants. *J Biomed Biotechnol* 8: 69036.
88. Ueno T, Tsukimura N, Yamada M, Ogawa T (2011) Enhanced boneintegration capability of alkali- and heat-treated nanopolymorphic titanium in micro-to-nanoscale hierarchy. *Biomaterials* 32: 7297-7308.
89. Ogawa T, Saruwatari L, Takeuchi K, Aita H, Ohno N (2008) Ti nanonodular structuring for bone integration and regeneration. *J Dent Res* 87: 751-756.
90. Li LH, Kong YM, Kim HW, Kim YW, Kim HE, et al. (2004) Improved biological performance of Ti implants due to surface modification by micro-arc oxidation. *Biomaterials* 25: 2867-2875.
91. Lim YW, Kwon SY, Sun DH, Kim HE, Kim YS (2009) Enhanced cell integration to titanium alloy by surface treatment with microarc oxidation: a pilot study. *Clin Orthop Relat Res* 467: 2251-2258.
92. Jeon O, Alsberg E (2013) Photofunctionalization of Alginate Hydrogels to Promote Adhesion and Proliferation of Human Mesenchymal Stem Cells. *Tissue Engineering* 19: 11-12.
93. Aita H, Att W, Ueno T, Yamada M, Hori N, et al. (2009) Ultraviolet light-mediated photofunctionalization of titanium to promote human mesenchymal stem cell migration, attachment, proliferation and differentiation. *Acta Biomater* 5: 3247-3257.
94. Tabuchi M, Ikeda T, Hirota M, Nakagawa K, Park W, et al. (2015) Effect of UV Photofunctionalization on Biologic and Anchoring Capability of Orthodontic Miniscrews. *Int J Oral Maxillofac Implants* 30: 868-879.
95. Crismani AG, Bertl MH, Celar AG, Bantleon HP, Burstone CJ (2010) Miniscrews in orthodontic treatment: review and analysis of published clinical trials. *Am J Orthod Dentofacial Orthop* 137: 108-113.
96. Hirota M, Ikeda T, Tabuchi M, Iwai T, Tohrai I, et al. (2014) Effect of ultraviolet-mediated photofunctionalization for bone formation around medical titanium mesh. *J Oral Maxillofac Surg* 72: 1691-1702.
97. Matsuura K, Utoh R, Nagase K (2014) Cell sheet approach for tissue engineering and regenerative medicine. *J Control Release* 19: 228-239.
98. Ishijima M, Hirota M, Park W, Honda MJ, Tsukimura N, et al. (2015) Osteogenic cell sheets reinforced with photofunctionalized micro-thin titanium. *J Biomater Appl* 29: 1372-1384.
99. Zhang Z, Wang K, Bai C, Li X, Dang X, et al. (2012) The influence of UV irradiation on the biological properties of MAO-formed ZrO₂. *Colloids Surf B Biointerfaces* 89: 40-47.
100. Sollazzo V, Pezzetti F, Scarano A, Piattelli A, Bignozzi CA, et al. (2008) Zirconium oxide coating improves implant osseointegration in vivo. *Dental Materials* 24: 357-361.
101. Tuna T, Wein M, Swain M, Fischer J, Att W (2015) Influence of ultraviolet photofunctionalization on the surface characteristics of zirconia-based dental implant materials. *Dent Mater* 31: 14-24.
102. Chevalier J (2006) What future for zirconia as a biomaterial? *Biomaterials* 27: 535-543.
103. Chevalier J, Loh J, Gremillard L, Meille S, Adolphson E (2011) Low-temperature degradation in zirconia with a porous surface. *Acta Biomater* 7: 2986-2993.
104. Att W, Takeuchi M, Suzuki T, Kubo K, Anpo M, Ogawa T (2009) Enhanced osteoblast function on ultraviolet light-treated zirconia. *Biomaterials* 30: 1273-1280.
105. Han Y, Yan Y, Lu C (2009) Ultraviolet-enhanced bioactivity of ZrO₂ films prepared by micro-arc oxidation. *Thin Solid Films* 517: 1577-1581.
106. Giljohann DA, Seferos DS, Daniel WL, Massich MD, Patel PC, et al. (2010) Gold nanoparticles for biology and medicine. *Angew Chem Int Ed Engl* 49: 3280-3294.
107. Dykman L, Khlebtsov N (2012) Gold nanoparticles in biomedical applications: recent advances and perspectives. *Chem Soc Rev* 41: 2256-2282.
108. Boisselier E, Astruc D (2009) Gold nanoparticles in nanomedicine: preparations, imaging, diagnostics, therapies and toxicity. *Chem Soc Rev* 38: 1759-1782.
109. Ghosh P, Han G, De M, Kim CK, Rotello (2008) Gold nanoparticles in delivery applications. *AdvDrug Deliv Rev* 1307-1315.
110. L Dykman, N Khlebtsov (2012) Gold nanoparticles in biomedical applications: recent advances and perspectives. *Chem Soc Rev* 41: 2256-2282.
111. Liang J (2013) Gold nanoparticles: emerging paradigm for targeted drug delivery system. *Biotechnol Adv* 31: 593-606.
112. K Niikura, T Matsunaga, T Suzuki, S Kobayashi, H Yamaguchi, et al. (2013) Gold nanoparticles as a vaccine platform: influence of size and shape on immunological responses in vitro and in vivo. *ACS Nano* 7: 3926-3938.